



# Purtop Easy



## One-component elastic polyurethane waterproofing membrane



### WHERE TO USE

For waterproofing:

- new roofs and repairs to existing roofs;
- terraces, balconies, walkways and pedestrian areas in general;
- green roofs.

**Purtop Easy** may be applied on:

- concrete;
- cementitious screeds;
- ceramic;
- fibre-cement boards;
- old bitumen membranes;
- metal.

### ADVANTAGES

- **Purtop Easy** forms a highly elastic and durable membrane (**Purtop Easy System Roof** has a certified service life of 25 years according to ETAG 005).
- **Purtop Easy** is a one-component, ready-to-use product and is very easy to apply.
- When **Purtop Easy** is admixed with **Purtop ADY** it may be applied in single 1.2 mm thick coat and has better mechanical properties and lower drying times.
- **Purtop Easy** maintains its mechanical properties at temperatures down to -40°C.

### TECHNICAL CHARACTERISTICS

**Purtop Easy** is a ready-to-use polyurethane aromatic waterproofing membrane, developed in MAPEI R&D Laboratories.

Once applied, in just a few hours **Purtop Easy** forms a seamless, elastic membrane with no overlaps and excellent crack-bridging properties which is

able to withstand normal dynamic stresses acting on structures.

Thanks to the complete range of primers available, **Purtop Easy** adheres perfectly to numerous types of substrate.

**Purtop Easy** has excellent mechanical characteristics that remain stable over the years, making the product highly durable.

**Purtop Easy** is easy to apply by trowel, roller or spray on horizontal, vertical and sloping surfaces.

**Purtop Easy** complies with the principles defined in EN 1504-9 (*"Products and systems for the protection and repair of concrete structures: definitions, requirements, quality control and evaluation of conformity. General principles for use of products and systems"*) and the requirements of the EN 1504-2 coating (C) according to principles PI, MC, PR, RC and IR (*"Surface protection systems for concrete"*).

**Purtop Easy** is a membrane certified for use as a liquid waterproofing system for roofs in compliance with ETAG 005 (refer to the **Purtop Easy System Roof** System data sheet).

### RECOMMENDATIONS

- Do not apply **Purtop Easy** if the ambient temperature is lower than +5°C or higher than +35°C or if it is about to rain.
- Do not apply if there is dew on the substrate.
- Do not apply **Purtop Easy** on substrates with rising damp or with more than 4% of residual moisture.
- Do not use on bitumen membranes that have only recently been applied (< 6 months). Always wait until the surface to be treated has completely oxidised.

**Purtop Easy: one-component polyurethane membrane for waterproofing terraces and roofs, in compliance with the requirements of EN 1504-2 coating ( C ) principles PI, MC, PR, RC and IR**

## TECHNICAL DATA (typical values)

### PRODUCT IDENTITY

|                               |                          |
|-------------------------------|--------------------------|
| Consistency:                  | thick liquid             |
| Colour:                       | white, grey, red         |
| Density (g/cm <sup>3</sup> ): | 1.4                      |
| Dry solids content (%):       | 82                       |
| Brookfield viscosity (mPa·s): | 3,000 (rotor 5 - 50 RPM) |

### APPLICATION DATA

|  |                |
|--|----------------|
| Application temperature:   | +5°C to +35°C  |
| Service temperature:   | -40°C to +80°C |
| Waiting time from application to putting into service at +23°C and 50% R.H. (hours): | 24             |

### MECHANICAL CHARACTERISTICS

|   |                                   |
|---|-----------------------------------|
| Elongation at failure (ISO 37) (%):             | > 400                             |
| Tensile strength (ISO 37) (N/mm <sup>2</sup> ): | ≥ 2 (≥ 4 with <b>Purtop ADY</b> ) |
| Tear strength (ISO 34-1) (N/mm):                | > 15                              |
| Shore A hardness (DIN 53505):                   | 50                                |

### FINAL PERFORMANCE DATA (1.2 mm thickness)

| Performance characteristics  | Test method    | Requirements according to EN 1504-2  | Performance of product (mixed with Purtop ADY)  |
|--|----------------|--|---|
| Permeability to water vapour:  | EN ISO 7783-2  | Class I $s_D < 5$ m<br>Class II $5 \text{ m} \leq s_D \leq 50$ m<br>Class III $s_D > 50$ m   | Class I<br>(average $s_D = 3$ m)  |
| Capillary absorption and permeability to water:                        | EN 1062-3      | $w < 0.1 \text{ kg/m}^2 \cdot \text{h}^{0.5}$  | average $w = 0.01 \text{ kg/m}^2 \cdot \text{h}^{0.5}$  |
| Permeability to CO <sub>2</sub> :                                      | EN 1062-6      | $s_D > 50$ m   | $s_D = 111$ m   |
| Direct traction adherence test:  | EN 1542        | <b>Flexible systems</b><br>with no traffic: $\geq 0.8 \text{ N/mm}^2$<br>with traffic: $\geq 1.5 \text{ N/mm}^2$   | 1.8 N/mm <sup>2</sup>   |
| Static crack-bridging at -10°C expressed as maximum width of cracking: | EN 1062-7      | from class A1 (> 0.1 mm)<br>to class A5 (> 2.5 mm)   | Class A4  |
| Dynamic crack-bridging at +23°C:                                       | EN 1062-7      | from class B1 to class B4.2  | Class B3.2  |
| Impact strength:   | EN ISO 6272-1  | No cracks or delamination after loading<br>Class I: $\geq 4$ Nm<br>Class II: $\geq 10$ Nm<br>Class III: $\geq 20$ Nm   | Class I   |
| Resistance to thermal shock (1x):                                      | EN 13687-5     | After thermal cycles<br>a) no swelling, cracking or delamination<br>b) average direct traction adherence test (N/mm <sup>2</sup> )<br><b>Flexible systems</b><br>with no traffic: $\geq 0.8 \text{ N/mm}^2$<br>with traffic: $\geq 1.5 \text{ N/mm}^2$                                     | 1.6 N/mm <sup>2</sup>   |
| Abrasion resistance (Taber test):                                      | EN ISO 5470-1  | Loss in weight less than 3000 mg with H22 abrasive disk/1,000 cycles/1,000 g load  | loss in weight < 2000 mg  |
| Exposure to artificial atmospheric agents:                             | EN 1062-11     | After 2,000 hours of artificial inclement weather:<br>no swelling according to EN ISO 4628-2<br>no cracking according to EN ISO 4628-4<br>no flaking according to EN ISO 4628-5<br>Slight colour variations, loss of brightness and crumbling may be acceptable                            | no swelling, cracking or flaking (colour change)  |
| Resistance to severe chemical attack:                                  | EN 13529       | Reduction of hardness less than 50% when measured according to the Shore method (EN ISO 868), 24 hours after removing the coating material from immersion in the test liquid<br>Class I: 3 days with no pressure<br>Class II: 28 days with no pressure<br>Class III: 28 days with pressure | NaCl 20%: class II<br>CH <sub>3</sub> COOH 10%: class II<br>H <sub>2</sub> SO <sub>4</sub> 20%: class II<br>KOH 20%: class II |
| Reaction to fire:  | EN 13501-1     | Euroclass  | E   |
| <b>FINAL PERFORMANCE</b>   |                |  |   |
| Resistance to root penetration (EN 13948):                             | no penetration |  |   |

- **Purtop Easy** is not suitable for surfaces that are continuously immersed.

## APPLICATION PROCEDURE

### Preparation of the substrate

All substrates, whether new or old, must be solid, clean, dry and free of all traces of oil, grease, old paint, rust, mould and any other material which could affect adhesion.

#### 1. Application on concrete substrates and cementitious screeds

Surfaces must be prepared according to specification by sand-blasting, shot-blasting, scarifying, bush-hammering or other methods, depending on which type of substrate the product is to be applied. Then treat the substrate with a suitable primer as follows.

Hollows, cavities and detached portions in the substrate must be repaired with suitable products from the **MapegROUT** and **Planitop** ranges. Choose the most suitable product according to the thickness to be repaired, the time available and the operating conditions on site.

After preparing the substrate, apply **Primer PU Fast** two-component polyurethane primer, or **Mapecoat I 600 W**, two-component epoxy primer in water dispersion, diluted at a 1:1 ratio with water, or **Primer SN** two-component, fillerized epoxy primer and then broadcast the surface while still wet with **Quartz 0.5**.

If the level of residual moisture in the substrate is higher than 4% and it is not possible to wait until it drops to a lower value, apply two or more coats of **Primer EP4 Fast**, two-component epoxy primer, depending on the condition of the substrate, until the pores in the substrate are completely sealed.

#### 2. Application on bitumen membranes

Clean the bituminous membrane to remove all traces of oil, grease, dirt in general and any other material which could affect adhesion of the primer, and remove all traces of dust with a vacuum cleaner or compressed air. The membrane must be perfectly dry before inspecting the surface and any damage in the membrane, such as blistering, tears or detached areas, must be repaired before applying the primer. Apply **Mapecoat I 600 W** two-component, water-based epoxy primer on all the horizontal surfaces and vertical hems with a roller or airless spray.

#### 3. Application on metal surfaces

Check the state of the substrate and dry sand-blast the surface to grade SA 2½ (according to Swedish Standards).

If it is not possible to dry sand-blast the substrate, prepare the surface using an alternative method, such as with a scrubbing-action or percussion-action cleaning machine.

Once the metal surfaces have been prepared as specified, apply **Primer EP 100W** two-component, water-based epoxy primer with a roller, brush or by airless spray, or alternatively **Mapedeck Primer 200** adhesion promoter for polyurethane systems, with a roller.

#### 4. Application on old ceramic floors

Old floors in ceramic, porcelain, clinker, terracotta, etc. must be well bonded to the substrate and must be completely free of any substances which could affect adhesion, such as grease, oil, wax, paint, etc. Prepare the surface with suitable tools and/or by sanding to remove traces of material that could affect adhesion of **Purtop Easy**.

Make sure the existing flooring is well bonded to the substrate and remove any areas that have become detached. Fill these areas and any empty grout lines with **Adesilex P4** cementitious skimming compound.

Prepare the surface as specified, apply **Primer SN** two-component, fillerized epoxy primer with a trowel or by spray and broadcast the surface while still wet with **Quartz 0.5**.

Before applying **Purtop Easy**, pay particular attention to the expansion joints, fillets between horizontal and vertical surfaces, which must be suitable treated. Structural joints have to be previously waterproofed with **Maiband TPE**.

#### Preparation of the product

**Purtop Easy** is a one-component, ready-to-use product but it is recommended to mix it before use to make sure it is perfectly blended.

If you decide to apply the product in a single coat it must be admixed with **Purtop ADY**, which is available in pre-dosed packs according to the various sizes of **Purtop Easy**.

#### Application of the product

After carefully preparing and priming the substrate, apply **Purtop Easy**. The temperature of the substrate must be at least 3°C above dew-point and the level of residual moisture must be no higher than 4%.

Apply at least two even coats of **Purtop Easy** with a trowel or roller to form a total thickness higher than 1.2 mm. If **Purtop Easy** has been admixed with **Purtop ADY**, a 1.2 mm thick layer may be applied in a single coat.

When the product is applied in two coats, it is possible to lay **Mapetex FG**, glass fibre reinforcing mesh, on the first coat while it is still wet. Wait until the first coat is completely dry before applying the second coat.

If application of **Purtop Easy** is interrupted and then taken up again after the maximum recoat time (24-48 hours), apply a coat of **Primer PU 60** and form an overlap at least 30 cm wide.

When applying **Purtop Easy** on vertical hems or on surfaces in general with a slope of more than 1.5%, it must be admixed with up to 3.6% in weight of **Additix P** thixotropising agent.

**Purtop Easy** may also be applied by airless spray if it hasn't been admixed with **Purtop ADY** or **Additix P**. When applying **Purtop Easy** by spray it must be diluted with 5-10% of **Thinner PU**.

# Purtop Easy



## Finishing off the membrane

If a non-slip finish or coloured finish that remains stable over time is required, coat **Purtop Easy** within 24-48 hours of application with **Mapecoat PU 20N** two-component, aliphatic polyurethane finish. Apply at least two coats and broadcast the surface with quartz sand, as indicated in the relative Technical Data Sheet. If a finish is not applied over the membrane, it may lose its colour or flake slightly.

If tiling is to be bonded on **Purtop Easy**, use **Kerabond** cementitious adhesive mixed with **Isolastic**, **Keralastic** epoxy-polyurethane adhesive or **Kerapoxy** epoxy adhesive.

## Cleaning

It is recommended to clean tools with water before the product starts to set. Once hardened, cleaning is much more difficult and must be carried out mechanically.

## CONSUMPTION

2 kg/m<sup>2</sup> corresponds to a dry coat around 1.2 mm thick.

In general, the consumption rates below are for a seamless film on a flat surface and will be higher on uneven substrates.

## PACKAGING

6, 15 and 25 kg drums.

## STORAGE

**Purtop Easy** may be stored for 12 months in its original packaging in a dry, covered area at a temperature of between +5°C and +35°C.

## SAFETY INSTRUCTIONS FOR PREPARATION AND APPLICATION

Instructions for the safe use of our products can be found on the latest version of the Safety Data Sheet, available from our website [www.mapei.com](http://www.mapei.com).

PRODUCT FOR PROFESSIONAL USE.

## WARNING

*Although the technical details and recommendations contained in this product data sheet correspond to the best of our knowledge and experience, all the above information must, in every case, be taken as merely indicative and subject to confirmation after long-term practical application; for this reason, anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application. In every case, the user alone is fully responsible for any consequences deriving from the use of the product.*

Please refer to the current version of the Technical Data Sheet, available from our website [www.mapei.com](http://www.mapei.com)

## LEGAL NOTICE

*The contents of this Technical Data Sheet ("TDS") may be copied into another project-related document, but the resulting document shall not supplement or replace requirements per the TDS in force at the time of the MAPEI product installation. The most up-to-date TDS can be downloaded from our website [www.mapei.com](http://www.mapei.com).*

**ANY ALTERATION TO THE WORDING OR REQUIREMENTS CONTAINED OR DERIVED FROM THIS TDS EXCLUDES THE RESPONSIBILITY OF MAPEI.**

**All relevant references for the product are available upon request and from [www.mapei.com](http://www.mapei.com)**



BUILDING THE FUTURE